Reflecta-White Plus[™]

LIGHT DIFFUSION & DUSTPROOF ROOMS

SUITABLE FOR ATTICS

Reflecta-White Plus[™] is the ultimate choice of insulation for increasing indoor reflective lighting performance. **Reflecta-White Plus[™]** contains an exposed ice white face and reinforced scrim foil backing with a thermo-cellular structure.

Reflecta-White Plus[™] can be effectively applied for light diffusion and as a decorative finish. Also, when included as part of the CRIS[™] or GI All-In- One[™] systems, **Reflecta-White Plus[™]** delivers both decorative and superior thermal performance.



KEY BENEFITS

- Reduced Cost of Roof Construction compared to Fragile Decorative Sarking
- White Surface lends to Better Light Diffusion than Reflective Aluminium Surfaces
- Able to be Cut to Length for Major Project
- Cost of Raw Materials More Stable than Foam ensuring Long Term Cost Competitiveness
- Able to be combined with any other GI Building Sciences[™] system for High Thermal Properties

SIZES - 30m² ROLLS

Reflecta-White Plus[™]- 20m L x 1.5m W roll



gibs.com.au

SPECIFICATIONS

Electrical Conductivity

	Reflecta-White Plus [™]	
Product Code	RW2156	
Silver Side Reflectance	97%	
Antiglare Side Reflectance	10%	
Roll Size	20m x 1.5m (30m²)	
Roll Diameter	370mm (±7%)	
Product Thickness	5.5mm (±0.5mm)	
Roll Weight	10.5kg (±7%)	

Declared Total R Values (m² K/W)

Heatflow	INWARD	OUTWARD
Small Roof	1.8	0.7
Large Roof	2.3	0.7
Material R-value at 23ºC	0.12	

All calculations are for unventilated roof and wall cavities

For specific calculation details please contact GI Building Sciences

These products meets the re	quirements of	AS/NZS 4200.1	Emittance
Duty	Extra Heavy		Silver Side
Vapour Classification	Class 2	Vapour Barrier	Antiglare Side
Vapour Permeability	0.0160 µg/N.s		Classifications in
Water Control Classification	Water Barrier		product should k
Flammability Index	Low (≤5)		Assessed by Jan
	i		•

Conductive

Emittance	Value	Classification	Category
Silver Side	0.03	IR Reflective	RN
Antiglare Side	0.09	IR Non-Reflective	RIN

in Accordance with AS/NZS 4200.1 & This be installed in accordance with AS 4200.2

mes Fricker This product conforms with AS/NZS 4859.1

PRODUCT TESTING

Testing Name	Testing Standard	Testing Result	
Thermal Performance	ASTM C518	0.12 (m²K/W)	
Flammability Index	AS 1530.2	≤5 (Low)	
Ignitability Index	AS/NZS 1530.3	0	
Spread of Flame Index	AS/NZS 1530.3	0	
Heat Evolved Index	AS/NZS 1530.3	0	
Smoke Developed Index	AS/NZS 1530.3	1	
Resistance to Dry Delamination	AS/NZS 4201.1	Pass	
Resistance to Wet Delamination	AS/NZS 4201.2	Pass	
Shrinkage	AS/NZS 4201.3	Comply	
Tensile Strength	AS 1301.448s	Extra Heavy Duty	
Edge Tearing Resistance	TAPPI T470 om-89	Extra Heavy Duty	
Surface Corrosion	AS/NZS 4859.1 App I	Pass	
Water Vapour Transmission	ASTM E96	Class 2, Vapour Barrier	
Resistance to Water Penetration	AS/NZS 4201.4	Water Barrier	
Emittance	AS/NZS 4201.5	Category: RN IR Reflective: Silver (0.03) IR Non-Reflective: White (0.9)	
Electrical Conductivity	AS/NZS 3100	Conductive	
Acoustic	ISO 354 AS ISO 11654 AS 1191 AS/NZS ISO 717.1	9 dB in 1/3 rd octave band	



Products are to be stored standing upright and on pallets not more than two high. Product warranty is voided for any product stored horizontally resulting in squeeze or crush. Returns of product displaying effects of deformation due to incorrect storage practices will not be accepted.

The product information included in this publication is provided in good faith in order to ensure the optimum performance of this In good latin in order to ensure the optimum performance or this product. However, no warranty is given or implied with respect to this information or the product itself regarding the product's suitability for any particular purpose, as factors outside our knowledge and control may affect its use. The usage of this and other building membranes will affect moisture migration in the building element. The purchaser is responsible for independently determining the suitability of the product for the intended purpose. GI Building Sciences Py Ltd reserves the right to amend product specifications without prior notice. Information provided is considered to be true and correct at the time of publication.

Issued July 2022



