

Reflecta-White Plus™


LIGHT DIFFUSION & DUSTPROOF ROOMS

IDEAL FOR ATTICS



Reflecta-White Plus™ is the ultimate choice of insulation for increasing indoor reflective lighting performance. Reflecta-White Plus™ contains an exposed ice white face and reinforced scrim foil backing with a thermo-cellular structure

Reflecta-White Plus™ can be effectively applied for light diffusion and as a decorative finish. Also, when included as part of the CRIS™ or GI All-In-One™ systems, Reflecta-White Plus™ delivers both decorative and superior thermal performance



NEW INSTALL PICS NEEDED

KEY BENEFITS

- ✓ Reduced Cost of Roof Construction Compared to Fragile Decorative Sarking
- ✓ White Surface lends to Better Light Diffusion than Reflective Aluminium Surfaces
- ✓ Able to be Cut to Length for Major Projects
- ✓ Cost of Raw Materials More Stable than Foam ensuring Long Term Cost Competitiveness
- ✓ Able to be Combined with any Other GI Building Sciences™ System for High Thermal Properties

30m² ROLL

Reflecta-White Plus™ - 20m L x 1.5m W roll

SPECIFICATIONS

Reflecta-White Plus™	
Product Code	RW2156
Silver Side Reflectance	97%
Antiglare Side Reflectance	10%
Roll Size	20m x 1.5m (30m ²)
Roll Diameter	370mm (±7%)
Product Thickness	5.5mm (±0.5mm)
Roll Weight	10.5kg (±7%)

Total R Values (m² K/W)

Heatflow	INWARD	OUTWARD
Small Roof	1.8	0.7
Large Roof	2.3	0.7
Material R-value at 23°C	0.12	

All calculations are for unventilated roof and wall cavities
For specific calculation details please contact GI Building Sciences

This product meets the requirements of AS/NZS 4200.1

Duty	Extra Heavy	
Vapour Classification	Class 2	Vapour Barrier
Vapour Permeability	0.0160 µg/N.s	
Water Control Classification	Water Barrier	
Flammability Index	Low (≤5)	
Electrical Conductivity	Conductive	

Emittance	Value	Classification	Category
Silver Side	0.03	IR Reflective	RN
White Side	0.90	IR Non - Reflective	

Classifications in Accordance with AS/NZS 4200.1 & This product should be installed in accordance with AS 4200.2

**Assessed by James Fricker
This product conforms with AS/NZS 4859.1**

PRODUCT TESTING

Testing Name	Testing Standard	Testing Result
Thermal Performance	ASTIM C518	0.12 (m ² K/W)
Resistance to Dry Delamination	AS/NZS 4201.1	Pass
Resistance to Wet Delamination	AS/NZS 4201.2	Pass
Shrinkage	AS/NZS 4201.3	Comply
Edge Tearing Resistance	TAPPI T470 om-89	Extra Heavy Duty
Surface Corrosion	AS/NZS 4859.1 App 1	Pass
Vapour Control Classification	AS/NZS 4200.1 Table 4	Class 2, Vapour Barrier
Resistance to Water Penetration	AS/NZS 4201.4	Water Barrier
Emittance	AS/NZS 4201.5	Category: RN IR Reflective: Silver (0.03) IR Non-Reflective: White (0.90)
Electrical Conductivity	AS/NZS 3100	Conductive
Acoustic	ISO 354 AS ISO 11654 AS 1191 AS/NZS ISO 717.1	9 dB in 1/3rd octave band
Surface Water Absorbancy	AS/NZS 4201.6	High
Vapour Permeability	ASTM E96	0.0160 µg/N.s
Flammability Index	AS 1530.2	Low (≤5)
Ignitability Index	AS/NZS 1530.3	0
Spread of Flame Index	AS/NZS 1530.3	0
Heat Evolved Index	AS/NZS 1530.3	0
Smoke Developed Index	AS/NZS 1530.3	1



FIRE SAFE



COMFORT, HEALTH & AMENITY



CONDENSATION CONTROL



SOUND PROTECTION



REDUCED POWER COSTS

Products are to be stored standing upright and on pallets not more than two high. Product warranty is voided for any product stored horizontally resulting in squeeze or crush. Returns of product displaying effects of deformation due to incorrect storage practices will not be accepted.

The product information included in this publication is provided in good faith in order to ensure the optimum performance of this product. However, no warranty is given or implied with respect to this information or the product itself regarding the product's suitability for any particular purpose, as factors outside our knowledge and control may affect its use. The usage of this and other building membranes will affect moisture migration in the building element. The purchaser is responsible for independently determining the suitability of the product for the intended purpose. GI Building Sciences Pty Ltd reserves the right to amend product specifications without prior notice. Information provided is considered to be true and correct at the time of publication.

Issued May 2023